



DURATION CR

Issue: 2.03
Effective: Apr. 30, 2005
Location: Carseland Production
MN-159

POLYMER COATED UREA

Type II 43-0-0 270 SGN

CHEMICAL ANALYSIS

	<u>MIN</u>	<u>MAX</u>	<u>TYPICAL</u>
TOTAL NITROGEN (wt. %N)	43.0		
• UREA NITROGEN (wt % N)	43.0		
BIURET (wt. %)			1.3
CONDITIONER (wt. % as Methylene Di-Urea)			1.2
MOISTURE (wt. %H ₂ O)			0.08
pH of 10% wt./wt. AQUEOUS SOLUTION			7.0
COATING WEIGHT (wt. %)			4.0

PHYSICAL ANALYSIS

COLOR			tan
ANGLE OF REPOSE (Degrees)			30
BULK DENSITY (kg per m ³ /lbs per ft ³)			
• LOOSE			769/48
SIZE GUIDE NUMBER (SGN)			270

AQUEOUS RELEASE ANALYSIS

ESTIMATED DAYS TO 80% RELEASE (23°C)	60	90
--------------------------------------	----	----

SCREEN ANALYSIS (% BY WEIGHT)

	<u>Tyler</u>	<u>Millimeters</u>	<u>Cumulative %</u>
	+6	3.35	0.6
	+7	2.83	18.1
	+8	2.36	87.9
	+9	2.00	99.7
	+10	1.70	100.0

Please obtain a Material Safety Data Sheet for more information.

To the best of the Manufacturer's knowledge and belief the information contained herein is accurate and reliable as of the date compiled. However, the Manufacturer makes no representation, warranty or guarantee as to the information's accuracy, reliability, completeness or timeliness. It is the user's responsibility to determine the suitability and completeness of such information for the user's own particular use or purposes. The Manufacturer does not accept any liability for any loss or damage that may occur from any use of this information.

Agrium Partnership, 13131 Lake Fraser Drive SE, Calgary, Alberta T2J 7E8; Phone: (403) 225-7000.

Agrium U.S. Inc., 4582 S. Ulster Street, Suite 1700, Denver, Colorado 80237; Phone: (303) 804-4400.